

Zirconia Toughened Alumina (Al₂O₃-ZrO₂) CeramAlloy™ ZTA







Material webpage



Overview

Zirconia Toughened Alumina (ZTA) is a high performance ceramic composite. It exhibits high hardness, strength, wear and corrosion resistance from its Alumina content, while still maintaining reasonably high fracture toughness from its Zirconia content.

Primary Advantages

-  High performance composite
-  Chemical inertness
-  Up to 1,500°C use temperature
-  Excellent wear resistance

Common Applications

- High Pressure Equipment
- Shaft Bearings
- Metal Forming Rollers & Guides
- Thread & Wire Guides
- Shaft Bushings
- Deep Well Down-Hole Valves & Seats

	Properties	Units	CeramAlloy ZTA
General	Composition	-	Alumina / Zirconia
	Color	-	White
Mechanical	Compressive Strength	MPa	2500
	Density	g/cm ³	4.1
	Flexural Strength @25°C	MPa	600
	Fracture Toughness K _{Ic}	MPa.m ^{1/2}	7
	Hardness (Vickers 500g)	GPa	16
	Young's Modulus	GPa	335
	Poisson's Ratio	-	0.23
Thermal	Thermal Conductivity @ 25°C	W/mK	20
	CTE @ 25°C – 400°C	10 ⁻⁶ /K	7
	Maximum Temperature (Air)	°C	1500
	Maximum Temperature (Inert)	°C	1500
	Thermal Shock Resistance ΔT	°C	200
Electric	Dielectric Strength DC @ 25°C	kV/mm	16
	Dielectric Constant @ 1MHz	-	10
	Volume Resistivity @ 25°C	ohm-cm	>10 ¹⁶

Disclaimer: The values presented are typical of those resulted from test samples. They are provided as an indication only to serve as guidance in the design of ceramic components and are not guaranteed. The actual values can vary according to the shape and size of the component.



PRECISION CERAMICS UK
uk@precision-ceramics.com
+44 (0)121 687 5858

PRECISION CERAMICS USA
info@precision-ceramics.com
+1 (727) 388 5060

PRECISION CERAMICS EU
eu@precision-ceramics.com
+353 51 550 480